

IMAPUR 1515/25 HR

DESCRIPTION Aliphatic one-component skin. One-solvent. Medium Polycarbonates based polyurethane. Excellent hydrolysis, abrasion and alcohol resistance

USE The product is used as top skin.

Characteristics of the product	<i>Aspect:</i>	Viscous liquid
	<i>Dry Content:</i>	25,00± 1%
	<i>Solvent/s</i>	DMF
	<i>Viscosity 25 °C:</i>	15.000 - 30.000 mPa.s

Physical characteristics of the dry film	<i>Modulus 100% (Kg/cm2):</i>	100
	<i>Modulus 300% (Kg/cm2):</i>	405
	<i>Tensile Stenght(Kg/cm2):</i>	535
	<i>Elongation(%):</i>	350

Modifiers	<i>For a matt effect</i>	IMASTER 20
	<i>For dilution</i>	DMF, IBA/TOL (MIX)
	<i>For the pigmentation</i>	NOVA TC ND
	<i>For the colouring</i>	IMACOLOR
	<i>To improve the spreading</i>	IMASI 20

Packing	<i>Metal drums of Kgs:</i>	200
----------------	----------------------------	-----

Storage The product must be stored at temperatures between -1 °C and 30 °C. In this conditions the product is stable for 6 months

Notes KEEP PACKINGS PERFECTLY SEALED
SHELTER FROM MOISTURE

Legend	N.A. = NOT APPLIABLE	N.D. = NON DETERMINED	F.C. = FORD CUP				
<i>First issuing date:</i>	21/09/2010	<i>Revision date:</i>	04/11/2014	<i>Revision nr.:</i>	2	<i>Print date:</i>	04/12/2020
